

ZIITEK ELECTRONIC MATERIAL & TECHNOLOGY CO.,LTD

TIF[™]700HU Thermally Conductive Gap Filler Pads Series

REV03



TIFTM700HU Series thermally conductive interface materials are applied to fill the air gaps between the heating elements and the heat dissipation fins or the metal base. Their flexibility and elasticity make them suited to coat very uneven surfaces. Heat can transmit to the metal housing or dissipation plate from the heating elements or even the entire PCB, which effecitly enhances the efficiency and life-time of the heat-generating electronic components.

ľ	eatures
٨	Cood thorm


- Sood thermal conductivity
- » Naturally tacky needing no further adhesive coating
- Soft and Compressible for low stress applications
- » Available in varies thickness

Application


- $\,\,$ Cooling components to the chassis of frame
- » Set Top Box
- » Car Battery & Power Supply
- » Charging Pile
- » LED TV/ Lighting
- » Graphics Card Thermal Module

Typical Properties of TIF [™] 700HU Series			
Property	Value	Test method	
Color	Gray	Visual	
Construction	Ceramic filled silicone elastomer	*****	
Thickness range	0.040"(1.0mm)~0.200" (5.0mm)	ASTM D374	
Hardness (Shore 00)	50±10	ASTM 2240	
Specific Gravity (g/cm³)	3.55	ASTM D792	
Operating Temp	-40~160℃	*****	
Dielectric Breakdown Voltage (T=1.0mm, Vac)	≥5500	ASTM D149	
Dielectric Constant@1MHz	4.5	ASTM D150	
Volume Resistivity	≥1.0X10 ¹² Ohm-cm	ASTM D257	
The sum of Conductivities (M/m/)	10.0	ASTM D5470	
Thermal Conductivity (W/mK)	10.0	ISO22007-2.2	
Flame Rating	94 -V0	UL E331100	

Pressure vs. Thermal Impedance



Pressure vs. Compression Ratio



Product Thicknesses: 0.040-inch to 0.200-inch (1.0mm to 5.0mm) **Product Sizes:** 8" x 16"(203mm x406mm)
Individual die cut shapesand and custom thickness can be supplied. Please contact us for confirming
Safe disposal method does not require special protection. The storage condition is low temperature and dry, away from open fire and away from direct sunlight. For detailed method, please refer to the product material safety data sheet.

Canada:

Tel:+001-604-2998559 E-mail: sales@thermazig.com China:
Tel: +86-769-38801208
E-mail: frances@ziitek.com.tw

Taiwan:
Tel:+886-2-22771007
E-mail:frances@ziitek.com.tw

